



MAIN CHARACTERISTICS OF ARAMID HONEYCOMB TYPICAL PROPERTIES FORM: Hexagonal - Rectangular							
			Compression	Plate Shear		Plate Shear	
Type	Cell (inch)	Weight (PCF)	Strength (PSI)	Strength (PSI*L*dir)	Strength (PSI*W*dir)	Modulus (KSI*L*dir)	Modulus (KSI*W*dir)
I	1/8	3.00	279.92	182.75	89.92	5.80	3.33
I	1/8	4.00	484.43	248.00	136.33	7.83	4.49
I	1/8	5.00	662.83	307.48	200.15	10.29	5.22
I	1/8	6.00	923.90	333.59	226.26	12.03	6.38
I	3/16	2.00	114.58	87.00	46.41	4.35	2.03
I	3/16	3.00	290.08	172.59	89.92	5.80	3.33
I	3/16	4.00	475.73	216.10	152.29	7.54	4.64
I	3/16	6.00	896.34	284.27	237.86	9.86	6.52

All the data furnished above is indicative.

Type: I = Industrial

Cell shape: Hexagonal

Cell dimensions: Is cell diameter, quoted in inches, e.g. 1/8 inch = (1/8 x 25.4) = 3.175mm

Weight: Is density in pounds per cubic feet, e.g. 3.00 pcf = (3.00 x 16) = 48.00 kg/m<sup>3</sup>

Max recommended processing temperature: 250o C

Recommended application temp range (for the final product:) -55o C ~ +175o C

Min sheet size: 2445 X 1250 mm

IMPORTANT NOTICE: Technical information furnished is based on laboratory findings and believed to be representative and correct. Fibremax Ltd makes no warranty for the information accuracy, including but not limited to, implied warranties of our product and relevant information for a specific performance, use or purpose. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user. FIBERMAX™ is a Fibremax Ltd company registered trade name. Use of the FIBERMAX™ trade name and other IP rights of Fibremax Ltd without written approval is strictly prohibited.

**SALES & ORDER PROCESSING**  
28<sup>th</sup> of October St No 8A, 37300  
Agria, Greece, EU

**EU ORDERING INFO**  
Tel: +302428092210  
Email: sales@fibremaxcomposites.com

Head office: Fibremax Ltd  
35 Grafton Way, W1T 5DB  
London, UK