



## Balanced, stabilized woven fabric data sheet

Code # C201Ps

Characteristics			
		Nominal	Tolerance
Mass per unit of area	(gr/sqm)	206	± 5%
Weave		Plain	
Laminate thickness	(mm)	0,19*	± 2,5%

Warp – Weft ratio		
	Warp	Weft
Fiber description	3K carbon fiber	3K carbon fiber
Thread count (ends/cm)	5	5
Weight distribution (g/mq)	100	100
Weight distribution (%)	48.55	48.55
Binder description	Copolyamide non woven, heat treated	
Binder (g/mq)	6	
Binder (%)	2.9	

(\*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.