



Balanced woven fabric data sheet

Code # C285T2

Characteristics			
		Nominal	Tolerance
Mass per unit of area	(gr/sqm)	285	± 5%
Weave		Twill 2X2	
Laminate thickness	(mm)	0,30*	± 2,5%

Warp – Weft ratio		
	Warp	Weft
Fiber description	3K carbon fiber	3K carbon fiber
Thread count (ends/cm)	7	7
Weight distribution (g/mq)	142,5	142,5
Weight distribution (%)	50	50

(*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.