



Balanced woven fabric data sheet

Code # C381S5 T400HB

| Characteristics | | |
|--------------------------------|----------|-----------|
| | Nominal | Tolerance |
| Mass per unit of area (gr/sqm) | 380 | ± 5% |
| Weave | Satin H5 | |
| Laminate thickness (mm) | 0,40* | ± 2,5% |

| Warp – Weft ratio | | |
|----------------------------|------------------------|------------------------|
| | Warp | Weft |
| Fiber description | 6K T400HB carbon fiber | 6K T400HB carbon fiber |
| Thread count (ends/cm) | 4,7 | 4,7 |
| Weight distribution (g/mq) | 190 | 190 |
| Weight distribution (%) | 50 | 50 |

(*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

