

Balanced woven fabric data sheet

Code # CK210T2

Characteristics		
	Nominal	Tolerance
Mass per unit of area (gr/sqm)	210	± 5%
Weave	Twill 2X2	
Laminate thickness (mm)	0,25	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	3K TR30S carbon fiber aramid 1260	3K TR30S carbon fiber aramid 1260
Thread count (ends/cm)	6,4	6,4
Weight distribution (g/mq)	Carbon 64,05 Aramid 40,95	Carbon 64,05 Aramid 40,95
Weight distribution (%)	Carbon 61 Aramid 39	Carbon 61 Aramid 39
Total weight rate (%)	50	50

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

