

Balanced woven fabric data sheet

Code # CM250T2

| Characteristics | | | |
|---|-----------|-----------|-------------|
| | Nominal | Tolerance | Norm |
| Mass per unit of area (g/m ²) | 250 | ± 5% | ISO 4605 |
| Weave | Twill 2x2 | | ISO 2113 |
| Laminate thickness (mm) | 0,26 | ± 2,5% | ISO 5084(*) |

| Warp – Weft ratio | | | |
|----------------------------|--|--|---|
| | Warp | | Weft |
| Fiber description | HR Carbon Fiber Grafil TR30- S - 3K 200 tex | | Anodized aluminum wire 6101/0,20 HR Carbon Fiber Grafil TR30- S - 3K 200 tex |
| Thread count (ends/cm) | 7,00 (ISO 4602) | | 9,00 (ISO 4602) |
| Weight distribution (g/mq) | Carbon 140 | | Anodized aluminum wire 50 Carbon 60 |
| Weight distribution (%) | Carbon 100% | | Anodized aluminum wire 45% Carbon 55% |
| Total weight rate (%) | 56% | | 44% |

(*) Theoretical thickness for an epoxy laminate with 40% reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

