



Woven fabric data sheet

Code # G146P

Characteristics		
	Nominal	Tolerance
Mass per unit of area (gr/sqm)	146	± 5%
Weave	Plain	
Laminate thickness (mm)	0,12*	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	Glass EC11 105 fiber	Glass EC11 105 fiber
Thread count (ends/cm)	7,5	6,4
Weight distribution (g/mq)	78,84	67,16
Weight distribution (%)	54	46

(*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.



FIBREMAX LTD
 35 GRAFTON WAY, W1T 5DB LONDON, UNITED KINGDOM
 TEL ++30 24280 92210, FAX ++30 24280 92270, info@fibermaxcomposites.com