



Balanced ballistic fabric data sheet

Code # K195P Thermostabilized

Characteristics				
		Nominal	Tolerance	
Mass per unit of area	(gr/sqm)	195	± 4%	UNI EN 12127
Weave		Plain		
Standard width	(mm)	1000	± 2,5%	
Laminate thickness	(µm)	260	± 15%	UNI EN ISO5084

Warp/weft characteristics			
Fiber description	Kevlar 129, 880 dtex	Kevlar 129, 880 dtex	
Thread count(ends/cm)	10,8 +-0,3	10,8 +-0,3	UNI EN 1049-2
Weight distribution (g/mq)	97,5	97,5	
Weight distribution (%)	50	50	
Tensile strength (N/cm)	Min 1600	Min 1600	UNI EN 13934-1

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

FIBERMAX Ltd
 28 Octovriou 8A , 37300 AGRIA MAGNISIA, GREECE
 TEL ++30 24280 92210, FAX ++30 24280 92270,
info@fibermaxcomposites.com