



Balanced woven fabric data sheet
Optimized for blunt trauma protection

Code # K290Ptm

Characteristics		
	Nominal	Tolerance
Total arial weight (gr/m ²)	293	± 5%
Weave	Plain	
Finish	Loomstate	
Stabization	Thermoplastic adhesive	
Laminate thickness (mm)	0,38	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	Aramid fiber 1100 dtex	Aramid fiber 1100 dtex
Thread count (ends/cm)	6,4	6,4
Weight distribution (g/mq)	146	146
Weight distribution (%)	50	50

Note: Technical information furnished is based on present knowledge and believed to be correct. No warranties of any kind are made. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

FIBREMAX LTD
35 GRAFTON WAY, W1T 5DB LONDON, UNITED KINGDOM
TEL ++30 24280 92210, FAX ++30 24280 92270, info@fibermaxcomposites.com