



## Balanced woven fabric data sheet

Code # K468P

Characteristics			
		Nominal	Tolerance
Mass per unit of area	(gr/sqm)	460	± 5%
Weave		Plain	
Laminate thickness	(mm)	0,64*	± 15%

Warp – Weft ratio		
	Warp	Weft
Fiber description	Aramid fiber 3300 dtex	Aramid fiber 3300 dtex
Thread count (ends/cm)	6,7	6,7
Weight distribution (g/mq)	230	230
Weight distribution (%)	50	50

(\*) Theoretical thickness of compressed epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.