

Balanced woven fabric data sheet

Code # KG390T2

| Characteristics | | |
|--------------------------------|-----------|-----------|
| | Nominal | Tolerance |
| Mass per unit of area (gr/sqm) | 390 | ± 5% |
| Weave | Twill 2X2 | |
| Laminate thickness (mm) | 0,41 | ± 15% |

| Warp – Weft ratio | | |
|----------------------------|------------------------------|------------------------------|
| | Warp | Weft |
| Fiber description | Glass 600 Aramid 2420 | Glass 600 Aramid 2420 |
| Thread count (ends/cm) | 4,8 | 4,8 |
| Weight distribution (g/mq) | Glass 117,00 Aramid 78,00 | Glass 117,00 Aramid 78,00 |
| Weight distribution (%) | Glass 60 Aramid 40 | Glass 60 Aramid 40 |
| Total weight rate (%) | 50 | 50 |

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

